



### Exercise 13: fracture

22.01.2024 - 26.01.2024

**Question 1** .....  
 A thick substrate of width  $w$  is coated with a thin film. The material of the film has Young's modulus  $E$  and Poisson ratio  $\nu$ . There is a crack of length  $a$  between substrate and film. Now the substrate is subjected to a tensile strain  $\varepsilon_0$ , which is therefore also imposed on the film. Calculate the energy release rate  $\mathcal{G}$ !




**Question 2** .....  
 An elastic film of thickness  $d$  and Young's modulus  $E$  is peeled at an angle  $\theta$  from a rigid substrate and a constant force  $F$ . During peeling the loose end of the film is stretched and stores elastic energy. This elastic energy is available for the creation of a new surface. Remember that the Griffith criterion for fracture is the hypothesis, that the new surface is created if the released elastic energy is larger than the energy required for making the new surface. We now consider the energy balance during release of the rubber film between points  $A$  and  $B$ .



- (a) Assume that  $w = 2\gamma$  is the work of adhesion, i.e. the magnitude of the energy per surface area that is required to separate the film from the substrate. What is the energy  $E_{\text{surf}}$  required to advance the film by  $\Delta c$ ?
- (b) Once released, the section  $A-B$  of the film is elongated with respect to its original length  $\Delta c$ . What is the elongation  $x = \varepsilon \Delta c$  (where  $\varepsilon$  is the strain) of that section of the film under the action of the force  $F$ ?
- (c) Compute the energy required for the extension of the section  $A-B$  of the film by integrating the elastic restoring force  $f(x)$  over the elongation of the film, i.e.  $E_{\text{el}} = \int_0^{\varepsilon \Delta c} dx f(x)$ . Write the final expression in terms of  $F$ .
- (d) Finally, the loose end of the film (to the left of point  $A$ ) gains potential energy because it moves parallel to the force  $F$ . By what distance  $\Delta x$  does the loose end move parallel to  $F$  when the film section  $A-B$  is released from the interface? (There is a purely geometric contribution to this distance and a contribution that comes from stretching the section  $A-B$ .)
- (e) Compute the potential energy by integrating the force  $F$  over this distance, i.e.  $E_{\text{pot}} = \int_0^{\Delta x} dx F$ .
- (f) Write down the total energy balance for this process. For this you need to consider which of the above processes release and which cost energy to determine their respective sign.
- (g) What is the critical force  $F$  required to peel the rubber film at an angle  $\theta$  from the glass substrate? Is there an angle at which peeling is no longer possible?

**Question 3** .....  
 A bar of length  $b$  and negligible mass is fixed at the ceiling and carries a much heavier body of mass  $m$ . Gravity

acts downwards and the gravitational acceleration is  $g$ . The bar has a cylindrical cross-section with a diameter  $D$ . It is made of a material with Young's modulus  $E$ , Poisson ratio  $\nu$  and critical stress intensity factor  $K_{Ic}$ . In the middle of the bar there is a circumferential notch of depth  $a = D/10$ . Determine the maximum mass  $m$  that the bar can sustain without breaking! Use the approximation for the stress intensity factor  $K_I$  that is shown in the figure!



**Question 4** .....

A cantilever beam of length  $L$ , thickness  $2b$  and width  $w$  is subjected to a normal force  $F$  at the end. The beam is made of a brittle material with critical stress intensity factor  $K_{Ic}$ , and contains a crack of length  $2a$  at the center. What is the maximum value of  $F$  at which the beam breaks? The stress intensity factor  $K_I$  for a plate with center crack of length  $2a$  under constant uniaxial tension is given in the figure.

